

Thermally conductive, two-part epoxy packaged in 1:1 cartridges

A two-part epoxy, 5340 delivers ease of application and doesn't settle during storage. The material features good dielectric properties, high lap-shear strength, and passes NASA outgas requirements. With its high lap-shear strength, 5340 Epoxy offers excellent adhesion, an important consideration for potting and bonding applications where keeping out moisture – and preventing potential delamination – is critical.

UNCURED	
Pot Life @ 25°C	90 Minutes
Viscosity, Part A, @ 25°C	115,000 cPs
Viscosity, Part B, @ 25°C	140,000 cPs
Viscosity, Mixed, @ 25°C	120,000 cPs
Thixotropic Index	1.6
Shelf Life @ 15-25°C	6 Months from Date of Shipment
Mix Ratio 100A-100B	Parts by Volume
Mix Ratio 100A-100B	Parts by Weight
CURED OPTIONS	2 hours @ 80°C 24 hrs @ 25°C (Handling) 7 Days @ 25°C (Full Cure)
CURED PROPERTIES	Based on cure of 2 hours @ 80°C
Color	Off-White
Shore D Hardness	90
Glass Transition Temp (°C)	70
Density (g/cc)	2.19
Lap Shear (psi)	2400
ELECTRICAL PROPERTIES	Based on cure of 2 hours @ 80°C
Dielectric Constant, 1MHz	4.44
Dissipation Factor, 1MHz	0.013
Dielectric Strength (volts/mil)	550
Volume Resistivity (ohm-cm)	1.7E+15@ 500 VDC
THERMAL PROPERTIES	Based on cure of 2 hours @ 80°C
CTE below Tg (ppm/°C)	35.7
CTE above Tg (ppm/°C)	114.6
Glass Transition Temp (°C)	70
Thermal Conductivity (W/mK)	1
Operating Temperature (°C)	-50 to 150
OUTGASSING PROPERTIES	Based on cure of 2 hours @ 80°C
TML (%)	0.42
CVCM (%)	0.02

KEY FEATURES

Electrically Insulative

Thermally Conductive

Convenient Mix Ratio

Flowable

✓ RoHS Compliant

Chat with a specialist:

service@appli-tec.com

603-685-0500 ext. 526

www.appli-tec.com

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev D

10-30-24

WVR (%)	0.16
ACOUSTIC PROPERTIES	
Velocity (m/s)	2909
Impedance (MRayls)	6.369
Loss (dB/cm-MHz)	-9.41
Density (g/cc)	2.19