

## 1.11 W/mK

The perfect choice for automated dispensing, Appli-Thane® 7308 maintains its dispensability for over 8 hours. The material can be cured during mass-reflow without disturbing the placement of components, thus eliminating several costly “component level” processing steps. It also eliminates the need for a separate cure cycle. The material meets NASA’s outgassing requirements and cures to a semi-flexible material with low modulus and a very low Tg. This material is thixotropic and maintains its form until subjected to temperatures exceeding 120°C.

<b>UNCURED</b>	
Work Life @ 25°C	8 hours
Viscosity @ 25°C	Paste
Shelf Life @ -40°C	12 Months
<b>CURE OPTIONS</b>	4 hrs @ 71°C    2 hrs @ 100°C 60 sec @ 200°C
<b>CURED PROPERTIES</b>	Based on cure of 4 hours @ 71°C
Color	Red
Shore A Hardness	86
Glass Transition Temp (C)	-34
Density (g/cc)	2.3
Lap Shear 2024T3 Clad (psi)	300
Tensile Strength (psi)	400
Peel Strength (lb/in.)	4
Cleavage Strength (lb/in width)	165
Tensile Modulus (psi)	1,200
Compressive Modulus (psi)	3,250
Elongation (%)	40
<b>ELECTRICAL PROPERTIES</b>	Based on cure of 4 hours @ 71°C
Dielectric Constant	7.3 @ 10 kHz    6.3 @ 100 kHz    5.07 @ 1 MHz
Dissipation Factor	0.121 @ 10 kHz    0.07 @ 100 kHz 0.042 @ 1 MHz
Dielectric Strength (volts/mil)	650
Volume Resistivity (ohm-cm)	1.0E 14@500 VDC
<b>THERMAL PROPERTIES</b>	Based on cure of 4 hours @ 71°C
CTE below Tg (ppm/°C)	50
CTE above Tg (ppm/°C)	120
Glass Transition Temp (°C)	-34
Operating Temp. Range (°C)	-100 to 125
Thermal Conductivity (W/mK)	1.11
Based on cure of 4 hours @ 71°C	

### KEY FEATURES

High Thermal Conductivity

Mass-reflow Curable

Electrically Insulative

Semi-flexible

Superior Thermal Cycling

Hydrolytic Stability

Ideal for Electrical Potting

Very Long Pot Life

Perfect for Automated Dispensing

Low Glass Transition Temperature

Low Modulus

Meets NASA Outgassing Requirements

Thixotropic

Solvent Resistant

Re-workable at Ambient Temperature

✓RoHS Compliant

### Chat with a specialist:

[service@appli-tec.com](mailto:service@appli-tec.com)

603-685-0500 ext. 526

[www.appli-tec.com](http://www.appli-tec.com)

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability

OUTGASSING PROPERTIES	
TML (%)	0.21
CVCM (%)	0.01
WVR (%)	0.1
ACOUSTIC PROPERTIES	
Velocity (m/s)	1,771
Impedance (MRayls)	4.062
Loss (dB/cm-MHz)	-14.85
Density (g/cc)	2.30

for incidental and consequential damages of any kind including but not limited to lost profits.

Rev F

12/19/2024